

DATASHEET (1/2)

Range:EMERGENCY AGMType name:TBE12-2,3Barcode:8436594880698







PE	RFORMANCES*	CONFIGURATION				
Voltage:	12 V	Size:	178x35x60 mm			
Capacity:	2,3 Ah (20h)	Polarity:	1			
Cap. 5/10/100h:	1,9/2,1/2,5 Ah	Terminal:	F1 (faston)			
Energy at 100h:	0,03 kWh	Holddown:	-			
Cycles at 50%:	500	Ventilation	Valve regulated (VRLA)			
Max. current:	34 A (5seg)	Maintenance:	Not required (MF)			
Int. Resistance:	90 mΩ					
Self-Discharge:	15 months					
	(from the date of production, at 25°C)					

*According to standards IEC 60254/60896

INTE	RNAL CONSTRUCTION	COMPONENTS				
Technology:	Manufacturer-sealed AGM	Container:	ABS/black			
		Lid:	ABS/black			
Alloy:	Calcium	Plugs:	Termal sealing, ABS/black			
Separator:	AGM (glass mat)	Handles:	-			
Total Weight:	1 kg					
Origin:	Asia					

RECOMMENDATIONS						
Storage:	Check voltage every 8 months.					
Recharge:	Use automatic chargers with constant voltage and AGM setup.					
Installation:	Use the apropriate cable section and length. Keep connections tight.					

CEMA Baterías is the exclusive importer for Europe of DECK Battery products



This document is not a contract and could be modified without notice. Any copy or distribution must be authorised by TECK Europe. Find more information at **www.teckeurope.com**

44230



DATASHEET (2/2)


Cyclic & Emergency Application Battery

TABLES & CHARTS


EMERGENCY AGM

TBE12-2,3


			TBE	12-2,3	Const	ant Cu	rrent L	Discha	rge (Ar	nperes	at 25	"C			
F.V/Time	5m in	10min	15min	20min	30m in	45m in	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	4.42	3.08	2.54	2.20	1.77	1.36	1.11	0.679	0.517	0.425	0.361	0.312	0.248	0.207	0.114
1.80V/cell	5.43	3.67	2.94	2.49	1.96	1.48	1.20	0.721	0.544	0.447	0.376	0.326	0.258	0.214	0.115
1.75V/cell	6.43	4.15	3.25	2.71	2.09	1 <mark>.</mark> 57	1.26	0.752	0.563	0.461	0.386	0.334	0.265	0.218	0.116
1.70V/cell	7.30	4.58	3.51	2.91	2.19	1.63	1.31	0.783	0.581	0.472	0.396	0.342	0.269	0.222	0.118
1.65V/cell	8.05	4.93	3.72	3.06	2.29	1.70	1.37	0.806	0.596	0.482	0.405	0.349	0.273	0.225	0.120
1.60V/cell	8.45	5.13	3.87	3.15	2.35	1.74	1.40	0.831	0.610	0.494	0.413	0.356	0.279	0.229	0.121
			TBE	12-2,3	Const	ant Po	wer Di	scharg	je (Wa	tts/cell) at 25	°C			
F.V/Time	5m in	10min	15min	20min	30m in	45min	1h	2h	3h	4h	5h	6h	8h	10h	20h
1.85V/cell	8.33	5.86	4.88	4.27	3.45	2.66	2.19	1.34	1.03	0.848	0.722	0.627	0.500	0.416	0.230
1.80V/cell	10.1	6.93	5.61	4.79	3.79	2.89	2.34	1.42	1.07	0.886	0.748	0.650	0.515	0.428	0.231
1.75V/cell	11.8	7.76	6.13	5.17	4.02	3.05	2.45	1.47	1.11	0.908	0.764	0.662	0.526	0.434	0.232
1.70V/cell	13.3	8.46	6.58	5.51	4.19	3.15	2.54	1.52	1.14	0.925	0.778	0.674	0.530	0.439	0.235
1.65V/cell	14.5	8.99	6.87	5.73	4.33	3.25	2.63	1.56	1.16	0.940	0.792	0.684	0.536	0.443	0.237
	14.9	9.24	7.08	5.84	4.41	3.29	2.67	1.60	1.18	0.957	0.803	0.694	0.545	0.448	0.237



Temperature Effects in Relation to Battery Capacity



Cycle Life in Relation to Depth of Discharge




B


EUROF

Ē


Float Charging Characteristics



Effect of Temperature on Long Term Float Life



Self Discharge Characteristics



A No supplementary charge required (Carry out supplementary charge before use if 100% capacity is required.)

Supplementary charge required before use. Optional charging way as below: 1.Charged for above 3 days at limited current 0.25CA and constant volatge 2.25ViceII. 2.Charged for above 20hours at limited current 0.25CA and constant volatge 2.45ViceII 3.Charged for 2-of bours at limited current 0.25CA.

C Supplementary charge may often fail to recover the capacity. The battery should never be left standing till this is reached.

44230

This document is not a contract and could be modified without notice. Any copy or distribution must be authorised by TECK Europe. Find more information at **www.teckeurope.com**