

DATASHEET (1/2)

Range:EMERGENCY AGMType name:TBE12-3,3Barcode:8436594880711





| - + | |
|-----|----|
| 0 | F1 |

| PE | RFORMANCES* | CONFIGURATION | | | | |
|------------------|--|---------------|------------------------|--|--|--|
| Voltage: | 12 V | Size: | 134x67x61 mm | | | |
| Capacity: | 3,3 Ah (20h) | Polarity: | 0 | | | |
| Cap. 5/10/100h: | 2,7/3/3,6 Ah | Terminal: | F1 (faston) | | | |
| Energy at 100h: | 0,05 kWh | Holddown: | - | | | |
| Cycles at 50%: | 500 | Ventilation | Valve regulated (VRLA) | | | |
| Max. current: | 48 A (5seg) | Maintenance: | Not required (MF) | | | |
| Int. Resistance: | 45 mΩ | | | | | |
| Self-Discharge: | 15 months | | | | | |
| | (from the date of production, at 25°C) | | | | | |

*According to standards IEC 60254/60896

| INTER | RNAL CONSTRUCTION | COMPONENTS | | | | |
|---------------|-------------------------|------------|---------------------------|--|--|--|
| Technology: | Manufacturer-sealed AGM | Container: | ABS/black | | | |
| | | Lid: | ABS/black | | | |
| Alloy: | Calcium | Plugs: | Termal sealing, ABS/black | | | |
| Separator: | AGM (glass mat) | Handles: | - | | | |
| Total Weight: | 1,4 kg | | | | | |
| Origin: | Asia | | | | | |
| | | | | | | |

| RECOMMENDATIONS | | | | | | | |
|-----------------|--|--|--|--|--|--|--|
| Storage: | Check voltage every 8 months. | | | | | | |
| Recharge: | Use automatic chargers with constant voltage and AGM setup. | | | | | | |
| Installation: | Use the apropriate cable section and length. Keep connections tight. | | | | | | |

CEMA Baterías is the exclusive importer for Europe of DECK Battery products



This document is not a contract and could be modified without notice. Any copy or distribution must be authorised by TECK Europe. Find more information at **www.teckeurope.com**

44230



DATASHEET (2/2)


Cyclic & Emergency Application Battery

TABLES & CHARTS

EMERGENCY AGM

TBE12-3,3

| | | | TBE | 12-3,3 | Const | ant Cu | rrent C | Discha | rge (Ar | nperes | s) at 25 | °C | | | |
|------------|-------|-------|-------|--------|--------|--------|--------------------|--------|---------|----------|----------|-------|-------|-------|-------|
| F.V/Time | 5m in | 10min | 15min | 20min | 30m in | 45min | 1h | 2h | 3h | 4h | 5h | 6h | 8h | 10h | 20h |
| 1.85V/cell | 6.14 | 4.28 | 3.53 | 3.06 | 2.46 | 1.89 | 1.55 | 0.944 | 0.719 | 0.591 | 0.502 | 0.435 | 0.345 | 0.287 | 0.158 |
| 1.80V/cell | 7.55 | 5.11 | 4.10 | 3.47 | 2.72 | 2.06 | 1.66 | 1.00 | 0.756 | 0.622 | 0.524 | 0.454 | 0.358 | 0.298 | 0.160 |
| 1.75V/cell | 8.95 | 5.78 | 4.52 | 3.77 | 2.91 | 2.19 | 1.75 | 1.05 | 0.783 | 0.641 | 0.538 | 0.465 | 0.368 | 0.303 | 0.162 |
| 1.70V/cell | 10.2 | 6.37 | 4.89 | 4.05 | 3.05 | 2.27 | 1.82 | 1.09 | 0.809 | 0.657 | 0.551 | 0.476 | 0.374 | 0.308 | 0.164 |
| 1.65V/cell | 11.2 | 6.85 | 5.17 | 4.25 | 3.18 | 2.36 | 1.90 | 1.12 | 0.829 | 0.670 | 0.563 | 0.485 | 0.380 | 0.313 | 0.167 |
| 1.60V/cell | 11.8 | 7.14 | 5.39 | 4.39 | 3.27 | 2.41 | 1.94 | 1.16 | 0.849 | 0.687 | 0.575 | 0.495 | 0.388 | 0.318 | 0.168 |
| | | | TBE | 12-3,3 | Const | ant Po | wer Di | schar | je (Wa | tts/cell |) at 25 | °C | | | |
| F.V/Time | 5m in | 10min | 15min | 20min | 30m in | 45m in | 1h | 2h | 3h | 4h | 5h | 6h | 8h | 10h | 20h |
| 1.85V/cell | 11.6 | 8.16 | 6.79 | 5.93 | 4.79 | 3.71 | 3.04 | 1.87 | 1.43 | 1.18 | 1.00 | 0.872 | 0.695 | 0.579 | 0.320 |
| 1.80V/cell | 14.1 | 9.64 | 7.81 | 6.66 | 5.27 | 4.01 | 3.26 | 1.98 | 1.49 | 1.23 | 1.04 | 0.905 | 0.716 | 0.596 | 0.322 |
| 1.75V/cell | 16.5 | 10.8 | 8.53 | 7.20 | 5.59 | 4.24 | 3.41 | 2.05 | 1.54 | 1.26 | 1.06 | 0.921 | 0.731 | 0.604 | 0.322 |
| 1.70V/cell | 18.5 | 11.8 | 9.15 | 7.67 | 5.83 | 4.38 | 3.53 | 2.12 | 1.58 | 1.29 | 1.08 | 0.938 | 0.738 | 0.610 | 0.326 |
| 1.65V/cell | 20.1 | 12.5 | 9.56 | 7.97 | 6.03 | 4.52 | <mark>3.6</mark> 6 | 2.17 | 1.61 | 1.31 | 1.10 | 0.952 | 0.746 | 0.616 | 0.329 |
| 1.60V/cell | 20.8 | 12.9 | 9.86 | 8.13 | 6.13 | 4.58 | 3.71 | 2.22 | 1.64 | 1.33 | 1.12 | 0.966 | 0.758 | 0.623 | 0.330 |



nperature(°C)

10.17C (F)

rent 0.25C max, voltage 2.45 ume:125% of discharged cap

Ambient 28°C (77

800

305

Cycle Life in Relation to Depth of Discharge

Charg

100% DOD


50% DOD

400


600

Number of Cycles


Float Charging Characteristics



Effect of Temperature on Long Term Float Life



Self Discharge Characteristics



A No supplementary charge required (Carry out supplementary charge before use if 100% capacity is required.)

entary charge required before use Optional charging way as belo d for above 3 days at imited current 0.25CA and constant volatge d for above 20 hours at limited current 0.25CA and constant volatg d for 8-16 hours at limited current 0.05CA. latge 2.25V/cell. В

C Supplementary charge may often fail to recover the capacity The battery should never be left standing till this is reached.

44230

B EUROF Ē

120

100

80

40

20

00

Capcity(%) 60

> This document is not a contract and could be modified without notice. Any copy or distribution must be authorised by TECK Europe. Find more information at www.teckeurope.com